

NORDIC WOOD PRESERVATION COUNCIL – NWPC

Technical Expert Group
 c/o Danish Technological Institute
 Att. Niels Morsing
 Gregersensvej, DK 2630 Taastrup, Denmark
 Phone: +45 72 20 23 12
 E-mail: nmo@teknologisk.dk



Date: 2023-07-01
 List no. 103

Wood preservatives and other wood protection systems approved by the Nordic Wood Preservation Council***

| Wood preservative | Retention requirement* in <i>Pinus spp</i> sapwood, kg/m ³ Class** | | | | Approval valid until | Certificate No |
|-------------------------------------|---|------|------|-----|-------------------------|-------------------|
| | M | A | AB | B | | |
| WATER-BORNE TYPE | | | | | | |
| CB + triazole products | | | | | | |
| Tanalith E3463/E3475 | - | 20.0 | 10.0 | - | 2023-12-31 | 200 |
| Bochemit Forte Profi | | 20.0 | 14.0 | | 2027-12-31 | 205 |
| ACQ products | | | | | | |
| Impralit-ACQ 1900 | - | 36.0 | 19.0 | - | 2027-12-31 | 87 |
| Impralit-ACQ 2200 | - | 22.0 | 12.0 | - | 2025-12-31 | 175 |
| Celcure AC 500 | - | 22.0 | 12.0 | - | 2025-12-31 | 183 |
| impralit-KDS 4 | - | 28.0 | 15.0 | - | 2025-12-31 | 154 |
| Impralit-KDS | - | 14.0 | 8.0 | - | 2025-12-31 | 203 |
| Celcure M65 | - | 22.0 | 10.0 | - | 2024-12-31 | 202 |
| Korasit KS2 | - | 20.0 | 12.0 | - | 2025-12-31 | 204 |
| Celcure MC-T3 | - | | 5.0 | - | 2025-12-31 | 207 |
| Celcure MC-T4 | - | 11.0 | 6.0 | - | 2026-12-31 | 209 |
| Quaternary ammonium products | | | | | | |
| Impralit-BKD | - | - | 10.0 | - | 2025-12-31 | 171 |
| Triazole products | | | | | | |
| Wolsit KD-10 | - | - | 5.0 | 3.5 | 2027-12-31 | 185 |
| Other water-borne products | | | | | | |
| Wolmanit CX-8 | - | 18.0 | 9.0 | 9.0 | 2025-12-31 | 162 |
| Wolmanit CX-8N | - | 18.0 | 9.0 | | 2027-12-31 | 199 |
| Wolmanit CX-8WB | - | 18.0 | 9.0 | | 2025-12-31 | 191 |
| Wolmanit CX-10 | | 15.0 | 7.0 | 7.0 | 2025-12-31 | 176 |

* The retention figure refers to the formulation specified by the preservative manufacturer.

** The Nordic wood preservation classes M, A, AB and B correspond to hazard classes 5, 4 and 3 (class B is intended for external joinery) respectively according to EN 335.

*** Wood protection systems are approved according to the NWPC approval system. The approval according to BPR (Biocidal Products Regulation) is done by the European and national authorities. NWPC do not take any responsibility with respect to the BPR approval.

| Wood preservative | Retention requirement* in <i>Pinus spp</i> sapwood, kg/m ³ Class** | | | | Approval valid until | Certificate No |
|--------------------------------------|---|-----|---------------------|---------------------|-------------------------|-------------------|
| | M | A | AB | B | | |
| ORGANIC SOLVENT TYPE | | | | | | |
| Triazole products[¤] | | | | | | |
| Protim P-Vac 11 | - | - | - | 26.0/0.41 a.i. | 2025-12-31 | 187 |
| OTHER OIL BASED PRODUCTS | | | | | | |
| Tanasote S40 | | 85 | 85 | | 2026-12-31 | 208 |
| CREOSOTE OILS | | | | | | |
| Creosote grade B | | 110 | 80 | - | running | EN 13991 |
| Creosote grade C | | 100 | 70 | - | running | EN 13991 |
| MODIFIED WOOD | | | | | | |
| ThermoTreat v 2.0 | | | >170° Min 1,5 hr | >170° Min 1,5 hr | 2027-12-31 | 206 |

[¤] The retention requirement is uptake of the formulation/active ingredients (a.i.) in kg per m³ sapwood in the treated zone.